

Rakoll® GXL 3

- Type of Product** PVAc adhesive, meets the requirements of class D 3 as a one-component product and mixed with Rakoll® GXL-3-Härter meets the requirements for D 4 standard DIN EN 204.
- Product Characteristics**
- good water resistance
 - quick setting time
 - if heat is applied, very short pressing times can be achieved
 - bonded joints with good high-temperature resistance
 - classification according to EN 204: load group D4 as a two-component system (ift certified)
 - classification according to EN 204: load group D3 as one-component system (ift certified)
 - adhesive strength according to DIN EN 14257 (WATT 91) as a one-component system (ift certified)
- Typical Applications** This product can be used for a variety of applications including:
- surface gluing of decor-finish film
 - veneering
 - high-frequency bonding
 - surface bonding of HPL/CPL in short cycle presses
 - carcass and assembly gluing
 - bonding joints in boards and block gluing of softwoods and chipboard as well as hardwoods
- Suitable substrates** Wood and wood-based material.

Typical Properties

Property	Value		
	Rakoll® GXL 3	Rakoll® GXL 3 Härter	Mixture
Base	PVA Dispersion	Polyisocyanate	-
Colour	white	colourless	white
pH	approx. 3	-	approx. 3
White point	approx. 7°C	-	approx. 7°C
Viscosity (Brookfield HB, Sp3, 20rpm, at 20°C)	approx. 13 000 mPa.s	-	approx. 11 500 mPa.s
Shelf life	9 months		

Application Instructions

Apply the adhesive thinly and evenly to one side or, if a high degree of water resistance is required, to both sides, using a spreading machine, glue roller, serrated trowel, glue brush and another suitable device.

Good results will be achieved if the following conditions are observed:

- Room and material temperature: 18°C – 20°C
- Moisture content of wood: 8 – 10%
- Relative humidity: 40 – 60%

Amounts of adhesive to apply:

- For surface bondings: 60 – 140 g/m²
- For assembly gluings: 160 – 180 g/m²

Open time at 150 g/m²: 8 – 10 minutes

Press pressure, depending on type of bonding: 0,1 – 0,8 N/mm²

Minimum pressing times:

Surface gluing of decor-finish film in short cycle presses: 5 – 10 seconds

High-frequency bonding with longitudinal heating: from 15 seconds

Gluing:

- Surface gluing of HPL/CPL in short cycle presses at +70°C: from 45 seconds
- Assembly gluing: 8 – 15 minutes
- Boards and block gluing: 10 – 15 minutes

Mixing ratio:

- 100 parts by weight of Rakoll® GXL 3 with 5 parts by weight of Rakoll® GXL 3 Härter

Mix the adhesive and the hardener together thoroughly.

Pot-life: approx. 12 hours at normal temperature. Temperatures above +20°C reduce the pot-life.

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience, and we believe this information to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

© and ™ are trademarks of H.B. Fuller Company ("H.B. Fuller") or one of its affiliated entities.

NOTE TO USER: *by ordering/receiving product, you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received this documentation. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, (1) the total aggregate liability of H.B. Fuller for any claim or series of related claims, however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability, or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. (2) H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill, or any indirect or consequential losses arising out of or in connection with product supply. (3) Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence, death, or personal injury caused by negligence, or for breach of any mandatory implied terms unless permitted by law.*



Application Instructions**Open time/Setting time:**

Strongly depend on working conditions such as temperature, humidity, absorpency of the materials being worked, and amounts applied.

Wood preparation:

All parts should mate well and be dust and grease free. Over tolerances will lead to longer setting times and weaker bonds. The joints should be cut shortly before bonding.

Presses:

Lay the items to be bonded together within the workable time and press them for as long a time as is needed to achieve the required initial firmness upon release. The pressure should be high enough to ensure contact of the parts over the entire area of the joint. Depending on the material and the type of bond being used, the mechanical firmness required for further processing of the parts is achieved within the shortest possible space of time. The higher levels of water resistance form more slowly and should be tested not earlier than 7 days after bonding.

Wood discolouration:

Because of the varied nature of wood components, e. g., depending on the area of growth and the type of pre-treatment, unpredictable discolouration may in some cases appear on different types of wood, such as beech, cherry and others. In addition, it is possible that iron together with the tannin in wood can cause discolouration, especially in the case of oak. We recommend you test this for yourself.

Advice:

Properties of storage tanks, pipelines and spreading devices made from steel, galvanised steel aluminium or other non-ferrous metals cannot be recommended due to the slightly acidic nature of the dispersion, as there is a danger of corrosion. For this reason, we recommend the use of storage tanks, pipes and spreading devices made from stainless steel or plastic (hard PVC, polyethylene, polyester resin).

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience, and we believe this information to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

© and ™ are trademarks of H.B. Fuller Company ("H.B. Fuller") or one of its affiliated entities.

NOTE TO USER: *by ordering/receiving product, you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received this documentation. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, (1) the total aggregate liability of H.B. Fuller for any claim or series of related claims, however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability, or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. (2) H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill, or any indirect or consequential losses arising out of or in connection with product supply. (3) Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence, death, or personal injury caused by negligence, or for breach of any mandatory implied terms unless permitted by law.*



Cleaning Instructions	Clean machines and utensils with water before the adhesive dries.
Typical Packaging	Please contact your local Sales Office for available packaging options.
Storage Conditions	Store the adhesive away from frost in tightly closed original containers at above +5°C. Storage temperatures in excess of +25°C considerably reduces the minimal storage time. This product can thicken a little after prolonged storage. The adhesive should then be thoroughly mixed and is then ready for use again.
Disposal Advice	Please refer to the MSDS for disposal instructions.
Safety Advice	Please refer to the MSDS for safety advice.

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience, and we believe this information to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

© and ™ are trademarks of H.B. Fuller Company ("H.B. Fuller") or one of its affiliated entities.

NOTE TO USER: by ordering/receiving product, you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received this documentation. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, (1) the total aggregate liability of H.B. Fuller for any claim or series of related claims, however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability, or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. (2) H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill, or any indirect or consequential losses arising out of or in connection with product supply. (3) Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence, death, or personal injury caused by negligence, or for breach of any mandatory implied terms unless permitted by law.

